

PCTWORLD INTELLEC
In

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09G 1/04, 1/06, 1/18	A1	(11) International Publication Number: WO 96/02600 (43) International Publication Date: 1 February 1996 (01.02.96)
(21) International Application Number: PCT/US95/08627 (22) International Filing Date: 10 July 1995 (10.07.95) (30) Priority Data: 08/275,905 15 July 1994 (15.07.94) US (71) Applicant: ARMOR ALL PRODUCTS CORPORATION (US/US); 6 Liberty, Aliso Viejo, CA 92656 (US). (72) Inventor: HOWE, Michael, W.; 22671 Baltar, Mission Viejo, CA 92691 (US). (74) Agents: BREZNER, David, J. et al.; Flehr, Hohbach, Test, Albritton & Herbert, Suite 3400, 4 Embarcadero Center, San Francisco, CA 94111-4187 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). Published <i>With international search report.</i>
(54) Title: WATER BASED PAINT PROTECTANT (57) Abstract A protective composition for automotive painted surfaces is provided, comprising emulsified silicone, an evaporation modifier and a dynamic surface tension reducer, dispersed in water.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

WATER BASED PAINT PROTECTANT

FIELD OF THE INVENTION

This invention relates to a protective composition suitable for use on painted surfaces, and in particular on cars.

BACKGROUND OF THE INVENTION

Many different types of automotive protectants are known in the art. For example, many different paste and liquid waxes are known. These products are applied to a clean surface and are rubbed or buffed to give a protective finish to the car. Such products generally require a minimum of 45 to 90 minutes for one person to apply, depending on the size of the car, and the application of a physical "buffing" force.

To overcome these disadvantages, several silicone-based treatments are on the market, such as "ZOIEG", "WATERLESS CAR WASH" AND "NEW FINISH". These products are organic solvent-based solutions of various silicones. These products relied upon high levels of solvents and abrasives to provide uniform film levels of silicone. These products generally do not show enhancement of color or gloss, and do not provide significant durability.

Thus it is an object of the invention to provide an easy to apply, water-based protectant which enhances color, gloss and durability of an automotive painted surface.

SUMMARY OF THE INVENTION

5 The invention provides an aqueous protective composition comprising emulsified silicone, an evaporation modifier, and a dynamic surface tension reducer, dispersed in water.

10 In one aspect, the emulsified silicone comprises dimethyl silicone, amino-functional silicone, and silicone resin, emulsified in water.

The invention also provides methods for protecting an automotive painted surface. The method comprises applying an aqueous protective composition to the automotive painted surface and wiping the surface to spread and dry the protectant.

15

DETAILED DESCRIPTION OF THE INVENTION

Typically, the desirable properties of a automotive protective composition are the enhancement of color, gloss and durability, as well as ease of application.

20

The present invention provides such an aqueous protective composition comprising emulsified silicone, an evaporation modifier, and a dynamic surface tension reducer, dispersed in water.

25 By "emulsified silicone" herein is meant an emulsion of one or more derivatized or underivatized silicone compounds such as dimethyl-containing silicones, amino-

functional silicones, and silicone resins. Preferably the emulsified silicone is a mixture of dimethyl silicone, amino-functional silicone, and silicone resin. The dimethyl silicone contributes the gloss and slip of the finish, i.e. the silky feel of the protectant. The amino-functional silicone deposits on or reacts with the painted surface, such that the silicone layer is firmly retained on the surface (e.g. by covalent or non-covalent bonding) and will not wash off easily. This contributes to the durability of the protectant. The silicone resin acts as a solidifier, to give the silicone layer more body, less mobility (i.e. such that it will not wipe off), and greater durability.

In the preferred embodiment, the range of acceptable molecular weights for the silicones is from about 500 to about 30,000. Generally, the higher the molecular weight of the silicone, the more wax-like properties are imparted, such as higher gloss, color enhancement, water-beading and durability. However, when the molecular weight is too high, the silicone becomes similar to conventional waxes with their attendant problems, such as difficulty of application.

In addition, amino-functional silicones vary in the number of derivatized amine groups. In the preferred embodiment, mid-level base equivalent amino-functional silicones are used.

Preferably, the emulsified silicone is dispersed in water, although some embodiments utilize other aqueous carriers.

The emulsified silicone ranges from about 15% to about 75% solids, with about 50% solids being preferred.

Accordingly, the dimethyl silicone can range from about 0% to about 100% of the solids in the emulsion, with about 20% to about 95% being preferred, and 89% being the most preferred. That is, in an emulsion that is 50% solids, dimethyl silicone provides 44.5% solids. The amino-functional silicone comprises from about 0% to about 100% of the solids in the emulsion, with about 1% to 10% being preferred, and 7% being the most preferred. That is, in an emulsion that is 50% solids, amino-functional silicone provides 3.5% solids. The silicone resin ranges from about 0% to about 20% of the solids in the emulsion, with about 0.05% to 10% being preferred, and 4.0% being the most preferred. That is, in an emulsion that is 50% solids, silicone resin provides 2% solids.

The silicone emulsion also contains a sufficient amount of one or more emulsifiers to maintain the silicone in emulsified form. Suitable emulsifiers include octyl phenol ethoxylate. It is desirable for the emulsion to have a proper hydrophilic-lipophilic balance (HLB). The desired HLB ranges from about 12.5 to about 14.5, with a preferred HLB of 13.4. This HLB is achieved using an octylphenol ethoxylate with an HLB of 8 and another one with an HLB of 18, with the percentage in the formula being 2.5 and 3, respectively. In one embodiment, the emulsifier in the emulsified silicone is of sufficient amount to allow the entire protective composition to be an emulsion; i.e. once formulated in the composition, the silicone is still emulsified. In alternative embodiments, the emulsifier does not cause the silicone in the protective composition to remain emulsified, and thus the silicone may settle out over time. In this embodiment, the composition is shaken or

stirred to evenly disperse the silicone solids within the composition prior to application.

5 The silicone emulsion ranges from about 2% to about 6% by weight in the protective composition, with about 2% to about 4% being preferred, and about 3.0% being the most preferred.

10 By "evaporation modifier" herein is meant a compound which modifies the rate of evaporation of the aqueous phase of the protective composition. If the rate of evaporation is too rapid, the composition will harden as it is applied, without allowing time for wiping and spreading. This results in the silicone layer being uneven and irregular. Similarly, the rate of evaporation cannot be too slow, since this allows drips to form, and dust and other debris to lodge in the silicone layer, detracting from the gloss and shine and leaving a smeary surface which may streak. Generally, the evaporation modifier must allow the applied composition to remain liquid and spreadable for at least about 1 minute, yet dry within about 3 minutes. In the absence of an evaporation modifier, the composition typically dries in about 15 seconds, depending on the environmental temperature and the temperature of the surface.

25 In some embodiments, the evaporation modifier will increase the evaporation rate. In other embodiments, the evaporation modifier will retard the evaporation rate. For example, if the dynamic surface tension reducer used in the composition increases the rate of evaporation of the composition, an evaporation modifier which retards the rate of evaporation will be used.

30

In addition, the evaporation modifier must not significantly alter the solubility of the silicone in the composition. If the solubility of the silicone is significantly increased, the silicone layer will wipe
5 off, causing irregularities in the silicone layer and a loss of protection. Similarly, the solubility of the silicone should not be decreased by the evaporation modifier, since this also results in a loss of protection.

10 In one embodiment, the evaporation modifier is a glycol ether. In a preferred embodiment, the evaporation modifier is either propylene glycol phenyl ether or ethylene glycol phenyl ether. Propylene glycol phenyl
15 ether is particularly preferred, since it results in high gloss and depth of color of the painted surface.

The evaporation modifier ranges from about 0.5% to about 3.5% by weight in the protective composition, with about 1% to about 3% being preferred, and about 2.0% being the most preferred.

20 By "dynamic surface tension reducer" herein is meant a compound which reduces the rate at which a low surface tension is achieved, in comparison to the compound without such reducer. A low surface tension of the
25 protective composition is necessary to wet the surface and promote spreadability, thus avoiding the formation of beads or drops on the surface. While silicone compounds generally do have low surface tension, they are very slow to spread due to their high viscosity. Accordingly, a dynamic surface tension reducer is
30 necessary to increase the spreading of the composition on the surface. Generally, in the absence of a dynamic surface tension reducer, the spray application of the

protective composition results in droplets or beads being deposited on the surface. Accordingly, the addition of the dynamic surface tension reducer causes the spray application of the composition to be a continuous and uniform sheet on the surface. However, the amount of the dynamic surface tension reducer should be adjusted such that the composition does not significantly run or drip prior to wiping.

Similar to the evaporation modifier, the surface tension reducer will not significantly alter the solubility of the silicone.

In a preferred embodiment, the dynamic surface tension reducer comprises n-octyl pyrrolidone. Other dynamic surface tension reducers include sarcosinates and dimethyl hexynol type materials.

The dynamic surface tension reducer ranges from about 0.05% to about 0.5% by weight in the protective composition, with about 0.05% to about 0.3% being preferred, and 0.10% being the most preferred.

The amount of water in the protective composition ranges from about 90% to about 98% by weight, with about 90% to about 96% being preferred, and 94.90% being the most preferred.

Preferably, the protective composition of the present invention is essentially free of abrasives, such as silicas, silicates, kaopolite or celite, normally found in silicone-based protectant products, nor volatile organic compounds or solvents.

Also the foregoing protectants may be loaded into aerosol or pump spray dispensers known in the art. In some embodiments, additional ingredients are added to the composition to facilitate aerosol application, also
5 as is well known in the art.

The composition may be applied to any automotive painted surface. The surface may be clean, dirty, new or moderately oxidized. The surface may be cool or hot.

The protective composition of the present invention may
10 be applied in a variety of ways. In a preferred embodiment, the composition is applied by aerosolization or pump spraying. However, the composition may be applied as a liquid as well. Generally, the composition is applied to portions of the surface at a time, to
15 prevent the composition from drying before wiping.

As soon as the composition is applied, the surface is preferably wiped, preferably using a clean dry cloth, to spread the composition as uniformly as possible. The surface is then rewiped lightly to dry, again preferably
20 using a clean, dry cloth.

When applied in this manner, the protective composition protects and beautifies the painted surfaces of a car without smearing or streaking. It provides a high gloss on the surface, and enhances the color of the surface.
25 It provides a durable, water beading surface. Durability is measured by the water-beading capabilities of the surface over time. A loss of shine may also indicate a loss of protectant.

The following examples serve to more fully describe the
30 manner of using the above-described invention, as well

as to set forth the best modes contemplated for carrying out various aspects of the invention. It is understood that these examples in no way serve to limit the true scope of this invention, but rather are presented for illustrative purposes.

Example 1
Preparation of a Protective Composition

A typical formulation of a protective composition is as follows:

10	Ingredient	Amount (% by wt.)
	propylene glycol phenyl ether	2.00
	n-octyl pyrrolidone	0.10
15	Emulsified silicone:	3.00 total
	a) dimethyl silicone	2.67
	b) amino-functional silicone	0.21
	c) silicone resin	0.12
	water	94.90

20 The propylene glycol phenyl ether was obtained from DOW. The n-octyl pyrrolidone was obtained from ISP. The dimethyl silicone was "WS101", obtained from Wocker, Inc. The amino-functional silicone was "F784" or "F785", obtained from Wocker, Inc. The silicone resin
25 was "VP1038", obtained from Wocker, Inc.

The composition was made as follows. First the emulsified silicone was made. This was done by blending the silicones, resins and surfactants together. The water was slowly added with non-shear agitation, with
30 mixing after all the water was added. Typical emulsions had a particle size of 150 μ to 350 μ , and preferably were in the 230 to 300 μ size.

The composition was applied via either pump spraying or aerosolization to a variety of automotive painted surfaces under various conditions, including clean, dirty and moderately oxidized surfaces. In addition,
5 the composition was applied both in full sunlight as well as in shade.

After application, a clean, dry cloth was used to spread the composition evenly. Then the surface was rewiped gently to dry the composition.

10 The treatment resulted in high gloss and color enhancement, with actual durability exceeding 4 weeks.

CLAIMS

1. An aqueous protective composition comprising emulsified silicone, an evaporation modifier, and a dynamic surface tension reducer, dispersed in water.
- 5 2. The composition of claim 1 wherein said emulsified silicone comprises dimethyl silicone, amino-functional silicone, and silicone resin, emulsified in water.
3. The composition of claim 1 wherein said evaporation modifier is a glycol ether.
- 10 4. The composition of claim 3 wherein said glycol ether is propylene glycol phenyl ether.
5. The composition of claim 1 wherein said dynamic surface tension reducer is n-octyl pyrrolidone.
- 15 6. The composition of claim 1 wherein said water comprises from about 90% to about 98% by weight.
7. The composition of claim 1 wherein said evaporation modifier comprises from about 0.5% to about 3.5% by weight.
- 20 8. The composition of claim 1 wherein said dynamic surface tension reducer comprises from about 0.05% to about 0.5% by weight.
9. The composition of claim 1 wherein said emulsified silicone comprises from about 2% to about 4% by weight.
- 25 10. The composition of claim 1 wherein said emulsified silicone contains roughly 50% solids, and said dimethyl

silicone comprises from about 10% to about 95% of the solids, said amino-functional silicone comprises from about 1% to about 10% of the solids, and said silicone resin comprises from about 0.05% to about 10% solids.

- 5 11. The composition of claim 1 which is substantially free of abrasives.
12. The composition of claim 1 formulated into an aerosol spray.
- 10 13. A pump spray dispenser containing the composition of claim 1.
14. A method of protecting an automotive painted surface comprising
- 15 a) applying to said surface an aqueous protective composition comprising water, a silicone emulsion, an evaporation modifier, and a dynamic surface tension reducer; and
- b) wiping said surface to spread said composition.
15. The method of claim 14 wherein said application is performed by pump spraying.
- 20 16. The method of claim 14 wherein said application is performed by aerosolization.
17. The method of claim 14 wherein said method further comprises
- c) rewiping said surface to dry said protectant.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US95/08627

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C09G 1/04, 06, 18

US CL : 106/2,3,10,287.11

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 106/2,3,10,287.11

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US, A, 5,017,221 (LEGROW ET AL.) 21 MAY 1991, col. 2, lines 15-20, col. 3, lines 26-37, 54-66, col. 4, lines 23-27, col. 5, lines 26-28.	1,2, 11-16
Y		3-10, 17

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	* T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
* A		document defining the general state of the art which is not considered to be of particular relevance
* E		earlier document published on or after the international filing date
* L		document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
* O		document referring to an oral disclosure, use, exhibition or other means
* P		document published prior to the international filing date but later than the priority date claimed
	* X	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
	* Y	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
	* G	document member of the same patent family

Date of the actual completion of the international search

28 JULY 1995

Date of mailing of the international search report

29 SEP 1995

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer
MARK BELL

Telephone No. (703) 308-3456